

# HyKote™ Sprayable Mastic

SEBS ROOF MASTIC



# IKO

## COMMERCIAL®

Specify with Confidence.



## HyKote Sprayable Mastic

SEBS ROOF MASTIC

HyKote SEBS Sprayable Mastic is a flexible, high-performance, puncture-resistant, liquid-applied styrene ethylene butylene styrene (SEBS) mastic. Ideal for use in various restoration and waterproofing applications, it provides durable, watertight protection when applied over existing systems.

### Product Highlights:

- Efficient – designed and specifically formulated to expedite spray application, especially on metal roofs during preparation of horizontal and vertical seams, expansion joints, penetrations, flashings and fastener heads.
- Reliable – Sprayable SEBS Mastic creates a strong, monolithic, self-flashing waterproofing membrane.

STOCK #:  
**10-SPMS-AL-05**

COLOR:  
**Almond**

SIZE/PACKAGING:  
**5-gallon Pail**

SUBSTRATES:  
**Granule-surfaced SBS or APP Modified Bitumen roofing membrane, galvanized metal, and may also be used on plywood, concrete, and BUR.**

*For questions about application over other substrates, please contact the Technical Services department.*

# HyKote™ Sprayable Mastic

SEBS ROOF MASTIC



# IKO

# COMMERCIAL®

Specify with Confidence.

## Surface Preparation:

- Inspect the substrate to determine suitability prior to beginning application.
- Surface must be dry, clean and free from dirt, loose rust and foreign substances.
- Certain surfaces may require abrading, scraping or pickling to ensure proper adhesion.
- Prime substrate using an appropriate HyKote Primer.
- An adhesion test may be required to ensure compatibility with the existing substrate.

## Application Methods:

- Sprayer, or tube assembly.

## Installation:

- Apply product using appropriate spray or tube assembly equipment (preferred methods) at ambient temperatures above 40° F (4° C). If spraying, remove all filters from spray unit or spray guns.
- Use heavy-duty (XHD) tips without a diffuser or atomizer bar. Tip sizes range from 441 to 447, 541 to 547 and 641 to 647. Tips may need to be adjusted depending on slope and product.
- Hold spray wand during application no higher than 12 inches from target substrate with 50% overlap and allow product to "FLOW" AND "SELF-LEVEL". Always spray at a straight "up and down" or 90-degree angle to enhance performance.
- There are certain exceptions to this rule such as for standing and vertical seam application. Always remix product after any application work stoppage of 20 minutes or more to ensure critical additive products stay in suspension.

**NOTE: For blisters, extreme membrane separation (greater than 3/16") or severely damaged repair areas, utilize HyKote SEBS Sprayable Mastic and a polyester reinforced scrim.**

## Minimum Coverage Rate:

- Surface dictates actual rate. Apply in one coat at a minimum of 42 wet mils per coat (1 gallon per 24 – 28 sq ft) for low slope surfaces.
- Substrate may dictate more than one coat due to severity (i.e., Alligatoring). This results in a finished coating with a minimum of 21 dry mils.

- Fastener encapsulation rate at approx. 250 individual units per gallon with a spray dollop on each unit. Vertical surfaces typically take two coats @ 42 wet mils each.
- One 5-gallon pail covers 120–140 sq ft in one coat per above.

## Clean Up:

Clean sprayers or tube assembly using regular mineral spirits.

*For questions about application or equipment, please contact the Technical Services department.*

## Storage and Handling:

Maintain materials in their original unopened containers with all labels intact and legible. Store containers on pallets in a covered or protected area. **Store in areas where maximum temperature does not exceed 90° F (32° C) and at a minimum of 40° F (4° C). Never store drums in an open environment without using a proper protective moisture-proof covering, as condensation or rain, under certain conditions, may infiltrate and contaminate the drum contents through the "bung" and ring areas. KEEP OUT OF REACH OF CHILDREN. KEEP AWAY FROM FLAME OR ANY OTHER SOURCE OF IGNITION.**

For additional safety and health information, refer to the Safety Data Sheet for this product.

## Technical Information:

Drying Time:	4-6 hours (typical) in optimal weather. Do not allow any flexing or foot traffic for at least 24 hours or curing mastic may rupture.
Shelf Life (in unopened container):	2 years

To the best of our knowledge and subject to change without prior notice, the technical values or data contained herein is true and accurate as of the date of issuance. The application instructions and recommendations contained herein are based on our knowledge of the products when properly stored, handled and applied under normal conditions, but no warranties, express or implied, are made of should be inferred with respect thereto or with respect to any values or statements made herein, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed in-house on a random basis and on a periodic basis by independent third party labs for the purpose of approval and/or classification. Acceptance, purchase and selection of these products are the sole responsibility of the buyer, buyer's agent or buyer's customer. Users should test this product to determine acceptability and suitability for their intended use. The manufacturer and distributor assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. Standard warranty is a 12-month Limited Material Warranty. NO OTHER GUARANTY OR WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, IS GRANTED, MADE OR IMPLIED.