

HyKote™ 5000

LOW VOC SEBS ROOF COATING



COMMERCIAL®

Specify with Confidence.



HyKote 5000

LOW VOC SEBS ROOF COATING

A low VOC, flexible, Hy-Performance, watertight, puncture resistant, ready-to-use single component, liquid-applied styrene ethylene butylene styrene (SEBS), liquid membrane. Used in various restoration and waterproofing liquid applied membrane applications.

Product Highlights

- **Low VOC** (Volatile Organic Compounds) Coatings contribute less to poor air quality which can have a detrimental effect on the public's health, as well as the environment.
- **Versatile** – HyKote SEBS coatings are easy to install and can be used as both a stop gap when repairing a section of a roof or reinforcing the entire surface of a commercial roofing project. SEBS coatings are an effective and lower cost option as compared to a full roof replacement.
- **Durable** – HyKote SEBS coatings provide very high tear and puncture resistance.
- **Flexible** – HyKote SEBS coatings have extremely high elasticity characteristics that allows for remarkable conformation to building movement and helps to reduce both premature aging and thermal shock.
- **Energy Savings** – HyKote SEBS coatings can be used to comply with Title 24, Part 6 SRI standards and thus are an excellent choice to help buildings save energy. Metal and other roofing materials absorb sunlight and heat throughout their life, and white SEBS applications help to reflect a majority of the sun's energy away from the building which may lead to energy savings.
- **Waterproofing** – HyKote SEBS coatings are formulated to provide maximum water resistance and due to their ultra-low moisture permeability, these coatings outperform acrylic coatings in their resistance to ponding or pooling water.

STOCK #(S):

50-RF-WH-05, 50-RF-WH-50, 50-RF-BL-05,
50-RF-BL-50, 50-RF-LG-05, 50-RF-LG-50

COLOR(S):

White, Black, and Light Gray
Custom or special-order colors may be requested based on availability.

SIZE(S)/PACKAGING:

5-gallon pails and 50-gallon drums.

SUBSTRATES:

Galvanized Metal, plywood, concrete, granulated-surfaced SBS, or APP Modified Bitumen, BUR.

For questions about application over other substrates, please contact the Technical Services department.

HyKote™ 5000

LOW VOC SEBS ROOF COATING



COMMERCIAL®

Specify with Confidence.

Surface Preparation:

- Surface must be dry, clean, and free from dirt, loose rust and foreign substances.
- Certain surfaces may require power washing starting at range up to 3750–4000 psi for metal and decreasing psi depending on substrate and/or conditions.
- Utilize wire brushing to remove loose mill scale, biomass, expended paint or coatings, corrosion or any other loose or foreign particulate.
- Certain surfaces may require abrading, scraping, or pickling to ensure proper adhesion.
- Certain surfaces must be cleaned and primed with a Manufacturer approved product.
- Existing target surface will dictate need for implementation of abrading and priming procedures. Depending on the substrate, moisture testing will need to be done prior to application.

Application Methods:

- Apply product using appropriate spray equipment (preferred method) or product may be rolled with a smooth-medium (1/4-inch to 3/8-inch nap) roller or soft brush at ambient temperatures above 40°F (4°C).
- If spraying, remove all filters from spray unit or spray guns.
- Use heavy-duty (XHD) tips without a diffuser or atomizer bar.
- Tip sizes range from 625 to 633 and 725 to 733.
- Tips may need to be adjusted depending on slope and product.
- *Note that it is always recommended to use a sprayer when a primer was applied to the substrate prior to coating application.*

Installation:

- Stir material thoroughly (summer and winter) prior to application. Always mix (stir) from bottom to top using a paddle type mixer making sure to keep the paddle under the surface to cut down on air infusion and potential air bubbles.
- Hold spray wand during application no higher than 12 inches from target substrate with 50% overlap and allow product to “FLOW” AND “SELF-LEVEL”.
- Always spray at a straight “up and down” or 90-degree angle to enhance performance.
- Always remix product after any application work stoppage of 20 minutes or more to ensure critical additives stay in suspension.

Minimum Suggested Coverage Rate:

- Apply in two coats at a minimum of 21 wet mils per coat (1.5 gallons per 100 sq. ft. per coat) for low slope surfaces.
- The combined two (2) coats result in a finished coating at a minimum of 21 dry mils. Vertical surfaces typically take 3 coats at 14 wet mils per coat to properly build final millage. One five-gallon pail covers 166 sq. ft. in two coats per above. One 50-gallon drum covers 1,666 sq. ft. in two coats per above.

Clean Up:

Clean spray equipment, brushes, rollers and tools using regular mineral spirits.

For questions about application or equipment, please contact the Technical Services department.

Storage and Handling:

Maintain materials in their original unopened containers with all labels intact and legible. Store containers on pallets in a covered or protected area. **Store in areas where maximum temperature does not exceed 90°F (32°C) and at a minimum of 40°F (4°C). Never store drums in an open environment without using a proper protective moisture-proof covering, as condensation or rain, under certain conditions, may infiltrate and contaminate the drum contents through the “bung” and ring areas. KEEP OUT OF REACH OF CHILDREN. KEEP AWAY FROM FLAME OR ANY OTHER SOURCE OF IGNITION.**

For additional safety and health information, refer to the Safety Data Sheet for this product.

Technical Information:

PHYSICAL PROPERTIES	
Weight, lbs./gal:	9
Solids (% by weight):	42
Viscosity @ 77°F, cps:	6,000 +/-500
VOC:	<90 g/L
Solar Reflectance Index - SRI (white only):	106 (initial), 91 (3 years)
Drying Time:	2-4 hours (typical) optimal weather conditions before recoating and 4-6 hours in non-optimal weather.
Shelf Life (unopened container properly stored):	2 years

PERFORMANCE PROPERTIES (FILM)	
Initial Elongation @73°F, %:	1,018
Initial Tensile Strength @ 73°F, psi:	1,700
Permeance, perms:	< 1.0
Water Swelling, Mass %:	< 1.0
Low Temperature Flex after 1000 hrs. accelerated weathering:	Pass
Appearance after 1000 hrs. accelerated weathering:	Pass

Approvals	
ANSI/UL 790 Test for Fire Resistance of Roof Coating Materials	
CRRC listed	

Unless otherwise stated, results are per ASTM D 6083 laboratory testing. Tested with, and without, primer. VOC testing above has been verified by 3rd party independent laboratory testing. Results vary consult so please contact the Technical Services department for details.

To the best of our knowledge and subject to change without prior notice, the technical values or data contained herein is true and accurate as of the date of issuance. The application instructions and recommendations contained herein are based on our knowledge of the products when properly stored, handled and applied under normal conditions, but no warranties, express or implied, are made of should be inferred with respect thereto or with respect to any values or statements made herein, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed in-house on a random basis and on a periodic basis by independent third party labs for the purpose of approval and/or classification. Acceptance, purchase and selection of these products are the sole responsibility of the buyer, buyer's agent or buyer's customer. Users should test this product to determine acceptability and suitability for their intended use. The manufacturer and distributor assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. Standard warranty is a 12-month Limited Material Warranty. NO OTHER GUARANTY OR WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, IS GRANTED, MADE OR IMPLIED.