

Torchflex™ TP-180-SF-Base (3.0 mm)

HEAT WELDED BASE SHEET

STOCK# 7750053

ROLLS PER PALLET: 32

PALLET SIZE: 132 cm x 112 cm

(52 in x 44 in)

LENGTH: 10 m (32.8 ft)

WIDTH: 1005 mm (39.6 in)

AREA: 10 m² (107.6 ft²)

MEMBRANE COVERAGE: 9.10 m² (98 ft²)

THICKNESS: 3.0 mm (118 mils)

SELVAGE: 90 mm (3.5 in)

Note: All reported values are nominal.



COMMERCIAL®

Specify *with Confidence.*



A durable and reinforced heat welded base sheet, let IKO Torchflex TP-180-SF-Base (3.0 mm) Heat Welded Base Sheet go to work for your next roofing project.

Torchflex TP-180-SF-Base (3.0 mm)

HEAT WELDED BASE SHEET

Reinforced

This product is made with a tough non-woven reinforced polyester mat strengthened with select glass fiber strands and coated top and bottom with select SBS polymers and premium quality asphalt to an approximate thickness of 3.0 mm (118 mils).

Non-Stick Surface

Torchflex TP-180-SF-Base sheet's top surface is sanded to prevent sticking in the roll during application.

Film Covered Bottom

The underside of the product is covered with a micro-perforated film surface that conveniently disappears upon torch welding to the substrate.

- SANDED SURFACE
- DURABLE

Torchflex™ TP-180-SF-Base (3.0 mm)

HEAT WELDED BASE SHEET



IKO COMMERCIAL®

Specify *with Confidence.*

Torchflex TP-180-SF-Base (3.0 mm) satisfies the requirements of CSA A123.23 Type B, Grade 3.

ISO 9001 - 2015 REGISTERED FACILITY

Please contact your IKO Technical Representative for specific slope requirements.

CHARACTERISTICS	UNITS	SPECIFICATION	TEST METHOD	TYPICAL PERFORMANCE
Strain Energy, (Before and After Heat Conditioning), @ 23°C (73.4°F) MD / XD:	kN/m (lbf/in)	CSA A123.23	CSA A123.23	> 5.5 (> 31)
Strain Energy, (Before and After Heat Conditioning), @ -18°C (0°F) MD / XD:	kN/m (lbf/in)	CSA A123.23	CSA A123.23	> 3.0 (> 17)
Peak Load, (Before and After Heat Conditioning), @ 23°C (73.4°F) MD / XD:	kN/m (lbf/in)	CSA A123.23	ASTM D5147	> 9.7 (> 55)
Peak Load, (Before and After Heat Conditioning), @ -18°C (0°F) MD / XD:	kN/m (lbf/in)	CSA A123.23	ASTM D5147	> 12 (> 68)
Elongation at Peak Load, (Before and After Heat Conditioning), @ 23°C (73.4°F) MD / XD:	%	CSA A123.23	ASTM D5147	> 22
Elongation at Peak Load, (Before and After Heat Conditioning), @ -18°C (0°F) MD / XD:	%	CSA A123.23	ASTM D5147	> 7
Ultimate Elongation, (Before and After Heat Conditioning), @ 23°C (73.4°F) MD / XD:	%	CSA A123.23	ASTM D5147	> 41
Mass Per Unit Area:	g/m ² (lb/ft ²)	CSA A123.23	ASTM D5147	2600 (0.53)
Dimensional Stability:	%	CSA A123.23	ASTM D5147	< 1.0
Low Temperature Flexibility:	°C (°F)	CSA A123.23	ASTM D5147	< -18 (< 0.4)
Compound Stability:	°C (°F)	CSA A123.23	ASTM D5147	> 102 (> 215)
Resistance to Puncture:	-	CSA A123.23	CSA A123.23	pass
Water vapour permeance:	Pa.s.m ² (perms)	N/A	ASTM E96 (Procedure B)	< 5.75 ng/Pa.s.m ² (< 0.1 perm)

IKO's products adhere to the industry standards of the jurisdiction in which they are sold by IKO. Numerical testing scores listed herein, if any, relate only to the samples tested and the standards & procedures listed herein. IKO does not guarantee that every IKO product will, upon similar testing, reveal an identical score to those set forth herein. IKO does not accept responsibility for any matters arising or consequences from the use of numerical testing.