

# Armourbond Flash Sand HD

SELF-ADHERING  
BASE SHEET FLASHING

STOCK# 7920024

ROLLS PER PALLET: 32

PALLET SIZE: 132 cm x 112 cm

(52 in x 44 in)

LENGTH: 10 m (32.8 ft)

WIDTH: 10 m (32.8 ft)

AREA: 10.05 m<sup>2</sup> (108.2 ft<sup>2</sup>)

MEMBRANE COVERAGE:

9.15 m<sup>2</sup> (98.5 ft<sup>2</sup>)

THICKNESS: 3.0 mm (118 mils)

SELVAGE: 90 mm (3.5 in)

Note: All reported values are nominal.



# COMMERCIAL®

Specify *with Confidence.*



Durable, reinforced and easy to install, let Armourbond Flash Sand HD go to work for your next commercial roofing project.

## Armourbond Flash Sand HD

SELF-ADHERING BASE SHEET FLASHING

### Tough

Armourbond Flash Sand HD incorporates a tough composite reinforcement of non-woven polyester strengthened with a glass fiber scrim in both machine and cross directions. It is coated top and bottom with select SBS polymers and premium asphalt to a thickness of approximately 3,0 mm (118 mils).

### Perfect for Flashing

Armourbond Flash Sand HD may be placed in flame-sensitive areas for base flashing details where a mopped or cold applied cap flashing will be used.

### Sand Coated Top, Film Release Bottom

The top surface of the product is coated with sand, while the self-adhering underside is covered by a removable silicone treated split release film.

- DURABLE
- SELF-ADHERING

# Armourbond Flash Sand HD

SELF-ADHERING  
BASE SHEET FLASHING



# IKO COMMERCIAL®

Specify *with Confidence.*



**Armourbond Flash Sand HD** satisfies the requirements of CSA A123.23 Type C, Grade 3.

*Minimum application temperature is -5 °C (23 °F) when membrane is properly conditioned to room temperature before application.*

ISO 9001 - 2015 REGISTERED FACILITY

Please contact your IKO Technical Representative for specific slope requirements.

CHARACTERISTICS	UNITS	SPECIFICATION	TEST METHOD	TYPICAL PERFORMANCE
Strain Energy, (Before and After Heat Conditioning), @ 23°C (73.4°F) MD / XD:	kN/m (lbf/in)	CSA A123.23	CSA A123.23	> 5.5 (> 31)
Strain Energy, (Before and After Heat Conditioning), @ -18°C (0°F) MD / XD:	kN/m (lbf/in)	CSA A123.23	CSA A123.23	> 3.0 (> 17)
Mass Per Unit Area:	g/m <sup>2</sup> (lb/ft <sup>2</sup> )	CSA A123.23	ASTM D5147	2200 (0.45)
Dimensional Stability:	%	CSA A123.23	ASTM D5147	< 0.5
Low Temperature Flexibility:	°C (°F)	CSA A123.23	ASTM D5147	< -18 (< 0.4)
Compound Stability:	°C (°F)	CSA A123.23	ASTM D5147	> 91 (> 195)
Resistance to Puncture:	-	CSA A123.23	CSA A123.23	pass

\*All rolls should be stored upright and indoors in a clean, dry area in their original unopened packaging. If stored outside, keep out of direct sunlight and extreme cold or hot temperatures, ensure original packaging is unopened.

IKO's products adhere to the industry standards of the jurisdiction in which they are sold by IKO. Numerical testing scores listed herein, if any, relate only to the samples tested and the standards & procedures listed herein. IKO does not guarantee that every IKO product will, upon similar testing, reveal an identical score to those set forth herein. IKO does not accept responsibility for any matters arising or consequences from the use of numerical testing.