

Metatech™ Detailer

LIQUID WATERPROOFING
MEMBRANE



IKO

COMMERCIAL®

Specify with Confidence.



Metatech Detailer

LIQUID WATERPROOFING MEMBRANE

STOCK# 02418510

SIZE: 10 kg (8.2 L),

QUANTITY PER PALLET: 50 pails

PALLET SIZE:

122 cm x 102 cm (48 in x 40 in)

CONSUMPTION RATE:

Min 4 kg/m² (3.28 ft²)

COLOUR: Stone Grey

Note: All reported values are nominal.
*May vary based on roughness of the surface.

IKO Metatech Detailer is a fibre-enriched, flexible and fast-curing two-component coating based on methacrylates.

- FAST-DRYING
- SEAMLESS MEMBRANE
- CATALYST ACTIVATED

IKO PMMA Technology

IKO, a global leader in roofing and waterproofing, has leveraged their world-wide technological roofing expertise to bring the latest liquid waterproofing roofing membrane to North America. IKO Metatech Detailer is a PMMA two-component rapid curing material ideally suited for challenging installations and repairs in tight areas.

Seamless Simplicity

IKO Metatech Detailer is a fibre-enriched, flexible and fast curing two-component coating based on methacrylates. IKO metatech Detail Fiber cures by adding the appropriate amount of catalyst (IKO Perkadox™).

Traffic Coating

IKO Metatech Detailer is used for critical details that are difficult to seal with a fully reinforced IKO metatech system, such as bolts, nuts and other penetrations of the surface.

Metatech™ Detailer

LIQUID WATERPROOFING
MEMBRANE



IKO

COMMERCIAL®

Specify with Confidence.

Technical Characteristics:

PROPERTY	UNIT	RESULT
Density:	g/cm ³	+/- 1.22
Viscosity(25°C, 1s-1):	-	3 – 5
Hardness(Shore A 23°C):	-	+/- 63
Tensile strength:	N/mm ²	+/- 4.5
Elongation:	%	+/- 240

Mixing Ratio:

SUBSTRATE TEMPERATURE	WEIGHT IKO METATECH CATALYST PER 10 KG PAIL	WEIGHT IKO METATECH CATALYST PER LITRE (1 KG = 0.82 LITRES)
3°C(37.4°F) to 5°C(41°F)	300 g	30 g per litre
6°C(42.8°F) to 15°C(59°F)	200 g	20 g per litre
16°C(60.8°F) to 40°C(104°F)	100 g	10 g per litre

The temperature of the substrate should remain min. 3°C higher than the dew point during application and curing.

Curing Time:

Pot life:	+/- 15 min.
Rain-proof:	+/- 30 min.
Can be walked on:	+/- 45 min.
Fully cured:	+/- 2 h.

Application:

Air temperature:	5°C - 35°C
Substrate temperature:	5°C - 40°C
Product temperature:	5°C - 30°C

IKO's products adhere to the industry standards of the jurisdiction in which they are sold by IKO. Numerical testing scores listed herein, if any, relate only to the samples tested and the standards & procedures listed herein. IKO does not guarantee that every IKO product will, upon similar testing, reveal an identical score to those set forth herein. IKO does not accept responsibility for any matters arising or consequences from the use of numerical testing.