

Metatech™ Surfacer

LIQUID WATERPROOFING
MEMBRANE



IKO

COMMERCIAL®

Specify with Confidence.



Metatech Surfacer

LIQUID WATERPROOFING MEMBRANE

STOCK# 02418610

SIZE: 10 kg (8.2 L).

QUANTITY PER PALLET: 48 pails

PALLET SIZE:

122 cm x 102 cm (48 in x 40 in)

CONSUMPTION RATE:

Smoothing fleece overlaps: 0.3 kg/m run

Filling: 1.7 kg/L

COLOUR: Pebble Grey

Note: All reported values are nominal.
*May vary based on roughness of the surface.

IKO Metatech Surfacer is a fast-curing two-component surfacer based on methacrylates.

- FAST-DRYING
- SMOOTHS OVERLAPS
- FILLS CRACKS AND JOINTS

IKO PMMA Technology

IKO, a global leader in roofing and waterproofing, has leveraged their world-wide technological roofing expertise to bring the latest liquid waterproofing roofing membrane to North America. IKO Metatech Surfacer is a PMMA two-component rapid curing material ideally suited to challenging floor installations and repairs in tight areas.

Seamless Simplicity

IKO Metatech Surfacer is a fast-curing two-component surfacer based on methacrylates. It is mainly used to prepare the substrate before IKO Metatech systems are applied.

Great for Smoothing Overlaps

IKO Metatech Surfacer is used to fill small cracks and joints as well as to smooth out areas of minor unevenness. With IKO Metatech Surfacer, overlaps of the IKO Polyester Fleece 110 re-inforcing fleece in the waterproofing layer can be smoothed out.

MetatechTM Surfacer

LIQUID WATERPROOFING
MEMBRANE



IKO

COMMERCIAL[®]

Specify with Confidence.

Technical Characteristics:

PROPERTY	UNIT	RESULT
Density:	g/cm ³	+/- 1.34
Hardness:	-	+/- 75

Mixing Ratio:

SUBSTRATE TEMPERATURE	WEIGHT IKO METATECH CATALYST PER 10 KG PAIL	WEIGHT IKO METATECH CATALYST PER LITRE (1 KG = 0.82 LITRES)
3°C(37.4°F) to 15°C(59°F)	400 G	40 g per litre
16°C(60.8°F) to 40°C(104°F)	200 G	20 g per litre
41°C(105.8°F) to 50°C(122°F)	100 G	10 g per litre

The temperature of the substrate should remain min. 3°C higher than the dew point during application and curing.

Curing Time:

Pot life:	+/- 15 min.
Rain-proof:	+/- 30 min.
Can be walked on:	+/- 45 min.
Fully cured:	+/- 2 h.

Application:

Air temperature:	-5°C - 35°C
Substrate temperature:	3°C - 50°C
Product temperature:	3°C - 30°C