

# MVP (Modified Vapour Protector)

VAPOUR RETARDER

STOCK# 7940002

ROLLS PER PALLET: 24

PALLET SIZE: 132 cm x 112 cm

(52 in x 44 in)

LENGTH: 32 m (105 ft)

WIDTH: 1000 mm (39.4 in)

AREA: 32 m<sup>2</sup> (344 ft<sup>2</sup>)

MEMBRANE COVERAGE: 29.26 m<sup>2</sup> (315 ft<sup>2</sup>)

THICKNESS: 1.2 mm (47.2 mils)

SELVAGE: 76 mm (3 in)

Note: All reported values are nominal.



 **COMMERCIAL**



Designed specifically as a vapour retarder, let IKO MVP Vapour Retardant go to work for your next roofing project.

## MVP (Modified Vapour Protector)

VAPOUR RETARDER

### Film Laminated

This vapour retarder is composed of modified SBS asphalt with a top surface of high density cross laminated polyethylene film.

### Designed for Multiple Deck Surfaces

IKO MVP is a self-adhering membrane used over various types of roof decks such as steel, concrete or wood.

### Pre-Insulation Installation

This product is designed as a vapour retarder before the installation of the roof system.

- STRONG
- SELF-ADHERING

# MVP (Modified Vapour Protector)

VAPOUR RETARDER



# COMMERCIAL

IKO Modified Vapour Protector conforms to CAN2-51.34M.

ISO 9001:2015 REGISTERED FACILITY

Please contact your IKO Technical Representative for specific slope requirements.



CHARACTERISTICS	UNITS	NOMINAL VALUE	TEST METHOD**	STANDARD LIMITS
Cold Flex:	°C (°F)	✓	ASTM D5147	MIN: -18 (0)
Water Vapour Transmission:	ng/(Pa·s·m <sup>2</sup> )	<1.5	ASTM E96-B	-
Tensile -Strength MD: XD:	kN/m (lbf/in)	✓ ✓	ASTM D5147	MIN: 8.78 (50) 3.5 (20)
Ultimate Elongation MD: XD:	%	✓ ✓	ASTM D5147	MIN: 20
Application Temperature:	°C (°F)	-	-	< -10 (14)

\*\* Although both ASTM and CGSB may have requirements for a particular test, only the more stringent is indicated. The information on this product information sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate. This product is not designed as a temporary waterproofing membrane.