



IKO TECHNICAL DATA SHEET

STOCK NO. 7910070

November, 2019

EdgeSeal

This product consists of a resilient, non-woven glass fiber mat, which is permeated and coated with SBS modified bitumen to a thickness of approx. 1.15 mm (45.2 mils). A silicon treated release film, which is easily removed during application, protects its self-adhesive backing on both sides. Edgesal is a “starter strip” that is designed to be used along the eave and rake. Product is designed and tested to comply with ASTM D1970.

CHARACTERISTIC	UNITS	NOMINAL VALUE	SPECIFICATION	TEST METHOD	STANDARD LIMITS	
ROLLS PER PALLET:	-	120	-	-	N/A	
ROLLS PER BOX	-	4	-	-	N/A	
PALLET SIZE:	cm (in)	132 x 112 (52 x 44)	-	-	-	
LENGTH:	m (ft)	20.5 (67.2)	-	-	± 1%	
WIDTH:	mm (in)	225 (8.86)	-	-	± 3 (1/8)	
THICKNESS:	mm (mils)	1.15 (45.2)	ASTM D1970	ASTM D751	MIN: 1.0 (40)	
TENSILE STRENGTH	MD: XD:	kN/m (lbf/in)	PASS PASS	ASTM D1970	ASTM D2523	MIN: 4.4 (25)
TEAR STRENGTH	MD: XD:	N (lbf)	PASS PASS	ASTM D1970	ASTM D4073	MIN: 89 (20)
THERMAL STABILITY (FLOW AT 70°C):	mm (mils)	PASS	ASTM D1970	ASTM D1204	MAX: 3.0 (118)	
COLD FLEX:	°C (°F)	PASS	ASTM D1970	ASTM D1970	MIN: -29 (-20)	
WATER VAPOUR PERMEANCE:	ng/Pa·s·m ² (perms)	PASS	ASTM D1970	ASTM E96	≤ 5.7 (≤0.1)	
SEALABILITY AROUND NAIL:	-	PASS	ASTM D1970	ASTM D1970	NO WATER PRESENT	

See also Material Information Sheet – MIS # 1201 Brampton

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.