



**STOCK NO. 7910075**

**March 2022**

## **IKO GOLDSEAM**

This superior self-adhesive seam tape is produced to a nominal thickness of 1.0 mm (39 mils). The sheet is surfaced with a unique treated film while a silicone treated release sheet, which is easily removed during application, protects its self-adhesive backing. The IKO GoldSeam tape can be applied over plywood or OSB seams as well as to cover gaps near fascia – near the eave. This product is designed and tested to comply with ASTM D1970.

CHARACTERISTIC	UNITS	NOMINAL VALUE	SPECIFICATION	TEST METHOD	STANDARD LIMITS
ROLLS PER PALLET	-	150	-	-	N/A
ROLLS PER CARTON	-	1	-	-	N/A
PALLET SIZE:	cm (in)	132 x 112 (52 x 44)	-	-	-
LENGTH:	m (ft)	20.3 (66.6)	-	-	± 1%
WIDTH:	mm (in)	108 (4.25)	-	-	± 3 (1/8)
THICKNESS:	mm (mils)	1.0 (39)	ASTM D1970	ASTM D5147	MIN: 1.0 (40)
ADHESION TO PLYWOOD AT 24°C (75°F)	kgf/30.5 cm (lbf/ft)	PASS	ASTM D1970	ASTM D903	MIN: 5.44 (12)
TENSILE STRENGTH MD: XD:	kN/m (lbf/in)	PASS PASS	ASTM D1970	ASTM D2523	MIN: 4.4 (25)
TEAR STRENGTH MD: XD:	N (lbf)	PASS PASS	ASTM D1970	ASTM D4073	MIN: 89 (20)
THERMAL STABILITY (FLOW AT 70°C):	mm (mils)	PASS	ASTM D1970	ASTM D1204	MAX: 3.0 (118)
COLD FLEX:	°C (°F)	PASS	ASTM D1970	ASTM D1970	MIN: -29 (-20)
WATER VAPOUR PERMEANCE:	ng/Pa·s·m <sup>2</sup> (perms)	PASS	ASTM D1970	ASTM E96	≤ 5.7 (≤0.1)
SEALABILITY AROUND NAIL:	-	PASS	ASTM D1970	ASTM D7349	NO WATER PRESENT

*The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation, and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.*