



IKO

TECHNICAL DATA SHEET

STOCK NO. 0670022

September, 2010

AM #15 LINED FELT

This product consists of a resilient, high-strength cellulose fiber mat that has been saturated with premium waterproofing bitumen to produce AM #15 Lined Asphalt Felt, a superior building material used specifically as a residential roofing underlayment. Line markings are positioned on the surface of the rolls to aid in the horizontal alignment of 3-tab metric shingles. This product complies with ASTM D4869 Type I in all respects, and satisfies building code requirements for an underlay felt (and eave protection when cemented in two plies). IKO's roofing products are produced and designed with consideration for environmental responsibility and sustainability, incorporating quality recycled components whenever possible, manufactured in facilities that comply with the most stringent government environmental regulations, and can therefore be a part of any "green" construction project.

CHARACTERISTIC	UNITS	NOMINAL VALUE	TEST METHOD	STANDARD LIMITS
QUANTITY PER PALLET:	-	36	-	N/A
PALLET SIZE:	cm (in)	107 x 107 (42 x 42)	-	-
LENGTH:	m (ft)	43.9 (144)	-	± 0.1%
WIDTH:	mm (in)	914 (36)	-	± 3 (1/8)
LINES:	mm (in)	57(2-1/4), 143(5-5/8), 200(7-7/8), 286(11-1/4), 343(13-1/2), 429(16-7/8), 486(19-1/8), 571(22-1/2), 629(24-3/4), 714(28-1/8), 772(30-3/8), 857(33-3/4)	-	± 3 (1/8)
SATURATION:	%	PASS	ASTM D228	MIN: 100
TENSILE STRENGTH	MD: kN/m (lbf/in) XD: kN/m (lbf/in)	PASS PASS	ASTM D146 ASTM D146	MIN: 5.25 (30) MIN: 2.63 (15)
PERMEANCE:	ng/(Pa•s•m ²) (grain/(ft ² •h•inHg))	PASS PASS	ASTM E96, PROC. A	MIN: 170 (3) MAX: 1400 (24)
PERMEANCE (AFTER ACC. AGING):	ng/(Pa•s•m ²) (grain/(ft ² •h•inHg))	PASS	ASTM E96, PROC. A	MAX: 2900 (51)

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.