


Asphalt Type 1

OXIDIZED BITUMEN



Asphalt Type 1

OXIDIZED BITUMEN

STOCK# 0760082

Note: All reported values are nominal.

For Damp Proofing and Waterproofing Applications

IKO Asphalt Type 1 is a proven waterproofing material and is suitable for use in selected damp proofing or waterproofing applications.

Designed for Multiple Uses

IKO's Type 1 Asphalt is an oxidized bitumen intended for use with organic felts, insulation and cover boards with slopes of 0 - $\frac{3}{4}$:12 (0-6.25%).

Available in Bulk

Processed under strict quality control standards in IKO's own oxidizing vessels, the product is available in bulk liquid.

Specially designed to alleviate moisture build up and easy to install, let IKO Asphalt Type 1 Oxidized Bitumen go to work for your next commercial roofing project.

- MINIMIZES MOISTURE
- MULTI-USE

Asphalt Type 1

OXIDIZED BITUMEN



COMMERCIAL



IKO's Asphalt Type 1 conforms to all requirements of CSA specification A123.4-M, Type I, and UL 55A requirements.

Please contact your *IKO Technical Representative* for specific slope requirements.

CHARACTERISTICS	UNITS	NOMINAL VALUE	TEST METHOD	STANDARD LIMITS
Softening Point:	°C (°F)	✓	ASTM D36	MIN: 60 (140) MAX: 68 (154)
Penetration @ 0°C (32°F):	dmm	✓	ASTM D5	MIN: 10
Penetration @ 25°C (77°F):	dmm	✓	ASTM D5	MIN: 30 MAX: 45
Flash Point:	°C (°F)	>274 (>525)	ASTM D92	MIN: 260 (500)
Solubility in TCE:	%	✓	ASTM D2042	MIN: 99.0
EVT* @ 75 cps:	°C (°F)	208 (406)	ASTM D4402	± 13 (25)
EVT* @ 125 cps:	°C (°F)	193 (379)	ASTM D4402	± 13 (25)

* Equiviscous temperature. See also Material Safety Data Sheet - MSDS # 1216 Brampton, MSDS # 1316 Calgary, MSDS # 1516 CRC (Toronto) and MSDS # 1816 Wilmington. The information on this product information sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.

