

# Asphalt Type 2

OXIDIZED BITUMEN



STOCK# **0760083**  
QUANTITY PER PALLET: **12**  
PALLET SIZE: **102 cm x 133 cm**  
**(40 in x 53 in)**  
SIZE: **100 lb**

Note: All reported values are nominal.

## Asphalt Type 2

OXIDIZED BITUMEN

### For Damp Proofing and Waterproofing Applications

IKO Asphalt Type 2 is a proven waterproofing material and is suitable for use in selected damp proofing and waterproofing applications.

### Available in Bulk and Kegs

Processed under strict quality control standards in IKO's own oxidizing vessels, the product is available in bulk liquid and 100 lb. kegs.

### Designed for Multiple Applications

IKO's Type 2 Asphalt is an oxidized bitumen intended for use with organic felts, glass felts, modified membranes, insulation and cover boards with slopes of 0-1:12 (0-8%).

Specially designed to alleviate moisture build up and easy to install, let IKO Asphalt Type 2 Oxidized Bitumen go to work for your next commercial roofing project.

- MINIMIZES MOISTURE
- MULTI-USE

# Asphalt Type 2

OXIDIZED BITUMEN



# COMMERCIAL



**IKO's Asphalt Type 2** conforms to all requirements of CSA specification A123.4-M, Type II, and UL 55A requirements.

Please contact your *IKO Technical Representative* for specific slope requirements.

CHARACTERISTICS	UNITS	NOMINAL VALUE	TEST METHOD	STANDARD LIMITS
Softening Point:	°C (°F)	✓	ASTM D36	MIN: 75 (167) MAX: 83 (181)
Penetration @ 0°C (32°F):	dmm	✓	ASTM D5	MIN: 10
Penetration @ 25°C (77°F):	dmm	✓	ASTM D5	MIN: 20 MAX: 30
Flash Point:	°C (°F)	>274 (>525)	ASTM D92	MIN: 260 (500)
Solubility in TCE:	%	✓	ASTM D2042	MIN: 99.0
EVT* @ 75 cps:	°C (°F)	243 (469)	ASTM D4402	± 13 (25)
EVT* @ 125 cps:	°C (°F)	212 (414)	ASTM D4402	± 13 (25)

\* Equiviscous temperature. See also Material Safety Data Sheet - MSDS # 1216 Brampton, MSDS # 1316 Calgary, MSDS # 1516 CRC (Toronto) and MSDS # 1816 Wilmington. The information on this product information sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.

