

Armourbond™ Flash HD

SELF-ADHERING
BASE SHEET FLASHING

STOCK# 7920012

ROLLS PER PALLET: 24

PALLET SIZE: 132 cm x 112 cm

(52 in x 44 in)

LENGTH: 15 m (49 ft)

WIDTH: 1005 mm (39.6 in)

AREA: 15 m² (161 ft²)

MEMBRANE COVERAGE: 13.66 m² (147 ft²)

THICKNESS: 2.5 mm (98 mils)

SELVAGE: 90 mm (3.5 in)

Note: All reported values are nominal.



IKO® COMMERCIAL



Durable, reinforced and easy to install, let Armourbond Flash HD go to work for your next roofing project.



Armourbond Flash HD

SELF-ADHERING BASE SHEET FLASHING

Tough

Armourbond Flash HD is composed of a tough composite reinforcement of non-woven polyester strengthened with a glass fiber scrim in both machine and cross directions. It is coated top and bottom with select SBS polymers and premium asphalt to a thickness of approximately 2.5 mm (98 mils).

Perfect for Flashing

Armourbond Flash HD may be placed in flame-sensitive areas for base flashing details where a heat fused cap flashing will be applied.

Film Coated Top and Release Bottom

A thin micro-perforated film covers the top surface of the product, while the self-adhering underside is covered by a removable silicone treated release film.

- DURABLE
- SELF-ADHERING

Armourbond™ Flash HD

SELF-ADHERING
BASE SHEET FLASHING



IKO® COMMERCIAL



Armourbond Flash HD satisfies the requirements of CSA A123.23-15 Type C, Grade 3.

ISO 9001 – 2008 REGISTERED FACILITY

Please contact your IKO Technical Representative for specific slope requirements.

CHARACTERISTICS	UNITS	SPECIFICATION	TEST METHOD	TEST PERFORMANCE
Strain Energy @ 23°C MD & XD:	kN/m	CSA A123.23	CSA A123.23	> 5.5
Strain Energy @ -18°C MD & XD:	kN/m	CSA A123.23	CSA A123.23	> 3.0
Elongation at Peak Load @ 23°C MD & XD:	%	CSA A123.23	ASTM D5147	> 2
Elongation at Peak Load @ -18°C MD & XD:	%	CSA A123.23	ASTM D5147	> 1
Ultimate Elongation Before Heat Conditioning @ 23°C MD & XD:	%	CSA A123.23	ASTM D5147	> 26
Ultimate Elongation After Heat Conditioning @ 23°C MD & XD:	%	CSA A123.23	ASTM D5147	> 9
Mass Per Unit Area:	g/m ²	CSA A123.23	ASTM D5147	> 2200
Dimensional Stability:	%	CSA A123.23	ASTM D5147	< 0.5
Low Temperature Flexibility:	°C (°F)	CSA A123.23	ASTM D5147	< -18 (0)
Compound Stability:	°C (°F)	CSA A123.23	ASTM D5147	> 91 (195.8)
Resistance to Puncture:	-	CSA A123.23	CSA A123.23	pass

The information on this product information sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.